



TILING FAMILY

TILING



Description

*Tiling standstone ceramic porphyre
This product is MONTANA type, Granito 1.
UPEC : U4 P3 E3 C2.
Grey colour (Pantone : Cool Gray 5C).
Pointing in the grey tone of the material.
Double gluing on tiled floor floated.*

Sizes

*30 x 30 cm.
45 x 45 cm.*

CLEANING OPERATION PROCEDURE

· 1st Cleaning (After laying)

TO DO	TO NOT DO
<ul style="list-style-type: none">· To wet the flooring before use of acid solution to impregnate the joints of water in order to avoid their corrosion.· Cleaning with a muriatic acid solution (diluted at 10 %) or with dedicated products for this operation (Casalgrande Deterprimo, Nelsen Viacal, Mapei Keranet, Kerakoll Deltaplus,) to remove remaining ciments and glue traces.· Large water rinsing, to.	<ul style="list-style-type: none">· If joints are not impregnated of water, they will be dissolved by the acid solution , giving a bigger porosity then a joint more difficult to lean et easier to stain.· To clean only with water : after drying, the tiled floor will seem dull.· If the flooring is not largely rinsed with water after « acid » cleaning, ciment milt and glue traces will reappear. Then the 1st cleaning.

CLEANING OPERATION PROCEDURE

- Routine cleaning

TO DO	TO NOT DO
<ul style="list-style-type: none">· Use ammionaque : AJAX, VIGOR, ...· Respect indicated dilutions on specifications & technical sheets of used products.· Use where it is possible a singlebrush machine (medium/hard disc). Cleaning tank must be separated of rinsing tank.· Proceed to an « acid » cleaning per month to remove limestone from rinsing water	<ul style="list-style-type: none">· This is totally forbidden to use cleaning products composed of saponifying agent (soap, linseed oil like Carolin). Those products make on surface a greasy film taht will keep dirtyness the flooring. More those products are used more it will difficult to remove this film.· To clean and rinse with the same tank (speaking about sigel-brush machine) is not efficient.· Clean everytime with an acid solution will destroy joints especially if the rinsing is not done correctly and a couple of times